

"FORCE AND WEAR ANALYSIS OF PVD COATED CUTTING TOOL" - A REVIEW

Jaimin P.Prajapati¹, Pina M.Bhatt², Naitik S.Patel³

¹Production Engineering (Mechanical Department), M.E.C, Mehsana- 384315, Gujarat, India

²Mechanical Department, R.K University, Rajkot, Gujarat, India

³Mechanical Engineering Department, M.E.C, Mehsana- 384315, Gujarat, India

Abstract

There are diverse types of cutting tackle in use for machining a variety of materials for the numerous operations in order to manufacture components. The manufacturers of these machinery imagine to improving their productivity, excellence of the components as well as longer life of the cutting tools. The device manufacturers also plan at producing excellence tools to with plunk for higher cutting forces, thermal resource resistivity with added wear resistance in addition to give longer living of the tool, to produce improved surface finish creation as well as maintain preferred dimensional accuracies of the product. Lots of researchers have studied tribological properties a variety of binary thin film materials to examine different properties like adhesion, rigidity and resistance coefficient according to the relevant applications. The special deposition techniques they used are disturbed Magnetron Sputtering, Ion Beam support Deposition, Physical Vapour Deposition etc. Lately ternary nitride based coatings are investigated as they exhibit improved tribological and mechanical properties compared to binary nitride based outside layer. This assessment paper is aimed to review tribological properties of two ternary nitride found coatings such as Titanium Aluminum Nitride along with Chromium Nitride.

Keyword :- Coating Material, Hard Coated, Wear, Cutting force.

INTRODUCTION

Thin coating of transition metal nitrides have been extensively used in several engineering function particularly due to their high rigidity, chemical dullness as well as excellent put on resistance. Surrounded by them, the properties and the function of TiN coatings have been deliberate extensively. The main weakness of TiN is its limited oxidation resistance (about 450–500°C). The adding together of other elements such as Al, Cr, Si, etc. add to the oxidation resistance of TiN^(1,2). TiAlN varnish have been developed for engineering function as an alternative to TiN seeing as 1986⁽³⁾. Accordingly, resources that can swap TiAlN are necessary. In the attempt of adding up Cr, research explain that a slight totaling of Cr to AlTiN results in excellent spiteful performance in the cutting of toughened steels⁽⁴⁾. The relationship stuck between the microstructure furthermore properties of nanocrystalline coatings otherwise thin coating nano complexed, which are based on nitrides of change metals, is the main topic of numerous studies⁽⁵⁾. This is also correct for chromium nitride varnish, which in addition contain aluminum and silicon.

Production enhancement of the engineering manufacturing is influenced by increasing necessities on quality, functionality in addition to robustness of cutting tools. The cutting tools should be prepared of material harder than the fabrics which are to be incise, as well as the device should be able to survive the heat produce in the metal-cutting progression. To produce excellence parts, a cutting instrument must have three characteristics: stiffness and power at high temperatures, toughness as well as wear resistance. So growth in the area of cutting tools is paying attention upon tool outside modification by advanced PVD technologies that are persistently improved, furthermore they are in general environmentally friendly for the reason that they do not need to use harmful chemical agents as well as gases. This reality stems from the standard of substance vanishing process of the substance, which is a origin of the final covering. The unique pro of advanced coatings of [Ti, Al_{1-x}Cr_x]N category is in their excellent properties, such as: very high corrosion resistance (above 900°C) with a elevated hardness of 38–50 GPa^(6,7). They are thermodynamically constant materials, also from the position of view of

granularity small piece growth does not happen even at temperatures above 1000°C. Grain boundaries act as an efficient barrier against imperfection propagation, along with high resistance of these materials is strong-minded in this method. Other positive features are the little coefficient of resistance, high thermal furthermore low chemical affinity to the machined substance^(8,9). Purpose of these coatings is possible to PVD tools using Cathodic curve technology^(10,11). The techniques explained make sure high wear struggle under high-speed work machining conditions when cutting device corrosion wear is dominant. The largely important cause of the high put on conflict of TiAlN and CrN coatings for the duration of high-speed machining is the arrangement of the protective alumina as well as chromium films on the cutting device surface⁽¹²⁾. Estimate of some properties of the structure thin layer-substrate requirements specific methods as well as procedures. The most significant mechanical properties from the point of outlook of this request are rigidity in addition to the adhesion of thin coating to substrate⁽¹³⁾.

The examine electron microscope (SEM) is the most widely used type of electron microscope. It examines microscopic structure by scanning the surface of materials, similar to scanning co focal microscopes but with much higher resolution and much greater depth of field. the most important feature of an SEM is the three-dimensional appearance of its images because of its large depth of field. For example, the depth of field can reach the arrange with tens of micrometers at $10^3\times$ magnification and the order of micrometers at $10^4\times$ magnification. An SEM is relatively easily operated and maintained, compared with a TEM⁽¹⁴⁾.

Scanning probe microscopy (SPM) is a system to observe resources with a solid investigate scanning the surfaces. The SPM is relatively new for materials characterization compared with light and electron microscopy. It examines surface features whose dimensions range from atomic spacing to a tenth of a millimeter. The SPM is considered the most powerful tool for surface structure examination currently available because it lets us 'see 'atoms'⁽¹⁴⁾.

LITERATURE REVIEW

J. Nickel et al (2000)⁽¹⁵⁾TiN-coated exercises. The flank put on measurements explain that the pre-nitrided drills had reduced line wear, as well as, hence, lengthened tool life, in association with the commercial drills, The quantitative numerical valuation of the side wear facts sets using non-parametric arithmetical tests also confirmed that, at a 95% self-assurance level, the pre-nitride drills had

longer device lives under all machining circumstances. The commercial maneuvers was attributed to the task of the plasma resources like nitriding in improving the TiN-coating affection, as well as, thus, increasing the wear conflict of the coating. TiN coating adhesion raises the wear resistance of the outside layer. Hardness charge of the HSS base substance of the category of drills wear equivalent. The wear skin texture of the chisel edge as well as its surroundings also long-established that the TiN-coating connection of the pre-nitrided instrument was stronger than that of the commercial instrument.

J. Wang (2000)⁽¹⁶⁾The effect of cutting tool hard surface coatings on the cutting forces and the associated force characteristics when turning a mild carbon steel has been presented. It has been shown that multi-layer hard surface coatings of cutting tools reduce the cutting forces, whilst the percentage reduction increases with an increase in the force components. A part from the coating type and substrate, the tool geometry and cutting conditions have been found to be important factors affecting the quantitative reductions of cutting forces by tool hard surface coatings. The empirical cutting force equations presented can be used for the selection and design of machine tools, cutting tools and textures as well as for the optimization of cutting conditions in process planning.

V. Fox et al (2000)⁽¹⁷⁾New solid lubricant coatings MoS₂@ and Graphit-iC@ offer many advantages over previous solid lubricant coatings because of their hardness, wear resistance and load-bearing capacity. They also have many advantages over conventional hard coatings because of their low friction and lubricating properties, which allows the component to be used at high speed, lowering the frictional forces and the temperature. MoS₂-titanium composite coatings are already used to improve the performance of cutting and cold-forming tools and are beginning to be used successfully for high speed dry machining. In cold-forming applications the use of the MoS₂-titanium composite coating has allowed the load applied during the process to be reduced. Work in dry condition reduces this requirement. MoS₂ and Graphit-iC@ are good candidates for a clean world process, and give greater productivity in machining, forming and for components.

G.S. Fox-Rabinovich et al (2001)⁽¹⁸⁾This coincides, as the rule, with a moment when a protective PVD-coating comes off contact faces of a tool. Under conditions of high loads and temperatures, partial oxidation of In will most likely start before

destruction of PVD-coating, still playing its protective role. It should be noted that the normal friction is characterized by the minimal depth of damage of the contact surface. Because of this, a small depth of the modified layer sharply effects on increasing of the tool life.

J. Richter et al (2001)⁽¹⁹⁾TiN as a monolayer or outer layer in coatings with a Ti under layer are characterized by thickness homogeneity (variation coefficient ranging from 2.89% to 9.76%), whereas the titanium under layers exhibited considerably less thickness homogeneity with the variation coefficient up to 28%. This results from an uneven profile of the Ti-TiN boundary rather than that of the Ti-substrate; it may contribute to higher adhesion and consequently better service properties of the coated cutting edges.

L.A. Dobrza'nski et al (2004)⁽²⁰⁾Coatings of the TiN+ mono otherwise multi + TiN structure deposited with the PVD technique in the cathodic semicircle evaporation CAE procedure on top of the substrates of cermets as well as cemented carbides demonstrate improved working properties than the commercially available device materials through the single and multiple-layer, as well as single- along with double part coatings deposited together in the PVD also CVD processes. Device cermets also cemented carbides among the TiN+ mono otherwise multi TiAlSiN + TiN system covering deposited with the PVD process in the cathodic arc vanishing course CAE qualify for the extensive industrial use on cutting instruments, offering the possibility to use them in the pro-ecological dried out cutting method.

G.S. Fox-Rabinovich et al (2004)⁽²¹⁾The effects on tool life were investigated for five pairs of elements that were ion-mixed into the base surface of the HSS substrate. The best wear resistance was shown for the 'triplex' coating with the (Ti+N) ion mixed sub layer. This is realized when the layer modified by Ti+N through ion mixing is applied. During cutting the oxygen-containing tribo-films are intensively developed on the surface of the ion-modified layer that protects the cutting tool.

A.E. Reite et al (2006)⁽²²⁾Comparison to CrN, CrC, TiAlN, TiN, It's CrN a slightly better behavior than CrC, but the tool also wears strongly. Breakouts and coating removal from the edge are obviously. The wear of the TiAlN coated tool is less severe in comparison to the first two coatings. The flank of the CrC coated tap is completely covered by the stainless steel material. Much better anti-adhesive properties are shown by CrN, TiAlN and TiCN. TiCN with the

highest abrasive wear resistance and obviously low tendency towards cold welding delivers the best result. Comparison to WC/C,DLC:-- The cutting torque of both coatings is very stable. The fluctuation is very low although the deviation is similar to TiAlN. Comparison to TiCN+DLC,TiCN+WC/C:-- The cutting edge of the TiCN+WC/C coated tap is more worn than the one of TiCN+DLC .The lower wear resistance of WC does not support. The coating remained very close to the edge . It is the coating of the lowest abrasive wear rate of all AlCrN coatings.

Recep Yigit et al (2008)⁽²³⁾The HTCVD multilayer coated insert has higher wear resistance, the wear life of the HTCVD multilayer coated insert compared with uncoated insert is calculated by ratio of the cutting time (t_2/t_1) when reaching the same flank wear. The HTCVD multilayer coated shows a great advantage for processing nodular cast iron. Uncoated carbide tool exhibits a slightly worse wear behavior than that of multilayer coated carbide tools at all cutting speeds. The best surface quality is obtained with HTCVD multilayer coated carbide tool (T_3) at all cutting speeds.

J. Gertha et al (2009)⁽²⁴⁾Two AlCrN-coated HSS hobs used to produce gears of structural steel by dry cutting. It represents the most common type of tool used in gear cutting. During cutting, a sharp front of complete coating removal initiates along the edge line and progresses on the rake face in the chip flow direction. The mechanisms of coating removal are decohesion or detachment of discrete fragments. At room temperature, the hardness of the layer (15 GPa) is significantly higher than the work material (1.7 GPa) but significantly lower than the AlCrN-coating (28 GPa). The smoothness of the layer, however, proposes that the material is very soft during cutting.

M. Sokovi c et.al. (2009)⁽²⁵⁾The TiAlN (PVD) coating displays the best adhesion (the highest critical load value $L_c = 76-80$ N). The maximum micro hardness ofHV0.07 = 4030MPawas observed in case of the (TiN +multi TiAlSiN + TiN) coating system deposited onto the ceramic substrate. Depositing hard PVD or CVD coatings onto the investigated CM ceramic tool inserts makes it possible to achieve: improvement of tool life, better quality of the machined surfaces, reduction of machining costs and elimination of cutting fluids used in machining.

F. Qin a et al (2009)⁽²⁶⁾Increasing coating depth will increase the outstanding stresses at the outside layer-substrate interface. In addition, increasing covering thickness will normally increase the confrontation of coating cracking as well as delimitation. Thicker

coatings will outcome in larger perimeter radii; Nonetheless, the amount of the effect on spiteful forces also depends ahead the machining situation. For the depth range tested, the living of diamond coated tackle increases with the glaze thickness because of hindrance of delamination.

M.A. ElHakim et al (2011)⁽²⁷⁾ These results could indicate greater adhesion between the c-BN cutting tool and the workpiece material, thus accelerating the wear rate more than for the Al_2O_3 , TiC and multilayer coated carbide tools. Comparison of the four different tool materials has been performed at cutting speed of 100m/min as it can be. In general, the wear rate on the flank face was served to be much greater than that on the rake face of the tools, overall in the C-BN cutting tools. The CCRs for chips produced from the coated carbide and the mixed alumina tools were found to be lower than that for the c-BN tools.

A.S.H. Basari et al (2011)⁽²⁸⁾ The ANFIS model that used linear output showed better performances compared to the constant output. The ANFIS model with 3 bell MFs in the input variables indicated the highest prediction accuracy with 98.09%. The ANFIS models with five MFs indicated higher RMSE and less R2 and prediction accuracy compared to the models with two and three MFs. Therefore, the small number of MFs is most suitable to be used in ANFIS modeling structure. The better agreement between the measured and predicted values of ANFIS model showed that the proposed ANFIS model can be a good option in predicting TiAlN flank wear.

D. Jakubczykova et al (2012)⁽²⁹⁾ Nano composite nAco coating prepared by advanced LARC technology had roughness parameters ~40% lower than monolayer AlTiCrN. This is connected with the composition of amorphous as well as nanocrystalline components of the sheet along with the method of LARC equipment. The deposited covering achieved brilliant hardness values. Decrease of coarseness assured superior hardness, the hardness rate (load 0.5 N) was ca 24 GPa for AlTiCrN layer along with ca 26 GPa for nAco sheet. Hardness assessments of the sample with deposited film are higher by 100% in association with the rigidity values of the substrate. Outcome gained by the pin-on-disc analysis indicated good quality adhesion assets of the covering along with minimal diversity in the friction coefficient for mutually layers at room temperature. Micro element for AlTiCrN 20°C, Ca201mm along with after testing at 400°C a little particle achieved the height of 250-350nm. Little particles detect on nAco coating max.80nm trying 20°C and later than 400°C testing height 105nm. resistance assessment of Ca 24GPa for AlTiCrN film, Ca 26 GPa for nAco layer. Extremely

good outcome was also attained by request at the nano compound layer merged by LARC.

Turgay Kivak et al (2012)⁽³⁰⁾ A result of experimental trials performed using the Taguchi OA, it was establish that the spiteful device was the most important factor affecting the face roughness with a percentage giving of 39.14%, and that the provide for rate was the nearly all noteworthy factor touching the thrust power with a proportion contribution of 82.77%.

J. Heinrichs et al (2012)⁽³¹⁾ Continuous and intermittent sliding promotes the same type of transfer with a central region, consisting of mainly transferred and oxidized Mn, Si and Al, surrounded by an outer region with an oxide layer with similar composition as the work material. On polished tool surfaces this transfer occurs on both TiN and AlCrN. Semi Polished Ra= 0.2µm, Rough Polished Ra= 0.3µm, Polished Tool Ra= 0.06µm, The small difference between the polished TiN and AlCrN coatings in were thus not observed for the rough resurfaces. There was no significant difference in appearance when comparing the TiN and AlCrN coatings.

Sergej N. Grigorieva et al (2012)⁽³²⁾ The concept of cutting tool material in the form of layered composite ceramics (LCC) with nano-scale multilayer coating (NMC) for machining hardened steels as well as hard-to machining Ni-alloys was developed and investigated. The LCC tools with NMC can be used for hardened steels machining with the use of cutting fluid, for dry cutting (H10-H20 ISO Standard), and for cutting hard to- machining heat-resistant Ni-alloys (S10-S20). The analysis of the LCC- NMC tools test results for the hardened steels and nickel alloys cutting allows for the following conclusions. The LCC-NMC tool life exceeds that of standard coated carbide tools and standard coated ceramic tools about 2.5-8.0 times. The developed coated LCC tools allows for increase of cutting productivity in 1.2-1.5 times not only in comparison with the coated carbide tools, but also in comparison with the coated ceramic tools.

Ping ChuanSiowa et al (2013)⁽³³⁾ The covered carbide slot in can be predicted to have longer living than uncoated carbide included. TiCN/ZrNv in addition to TiCN-coated carbide include had comparable moreover life as well as presentation with those of business TiCN-coated carbide add moreover they may achieve better than profit-making TiN-coated carbide add in valid machining request. The surface stability of the in-house developed

TiCN/ZrN with TiCN coatings was minor than to facilitate of marketable TiCN coating nevertheless higher than that of profit-making TiN coating.

J. Heinrichs et al (2013)⁽³⁴⁾The formation and build-up of tribofilms in an intermittent sliding contact between PVD coated HSS and case hardening steel have been studied for three different liding speeds. Two different commercial PVD coatings, TiN and AlCrN, were evaluated and the following conclusions could be made. With moderate speed, two tribofilms are formed separately. An area with very limited transfer of work material separates the two areas of oxidized material. The transferred material has the same appearance and chemical composition irrespective of coating type if moderate speeds are used. Low sliding speed results in an uneven transfer of steel. High sliding speed results in thermal softening of the substrate, which leads to coating failure and flaking;n.b.the coating is not worn; it is the substrate that is limiting. AlCrN provides better substrate protection at high speeds than TiN does.

D. Kottfera et al (2013)⁽³⁵⁾CrAlN & TiAlN monolayer lower roughness when compare to monolayer TiN and KTRN. TiAlN & KTRN coating which leads to achieve of higher hardness and better coating. The drill test of the coated bits showed suitability of TiAlN and KTRN coatings for drilling without cutting fluid at the selected conditions. The bit coated by TiN and CrAlN suffered significantly higher wear, which means significantly lower level of performance.

S. Sveen et al (2013)⁽³⁶⁾The scratch testing has been used in order evaluate the adhesion between arc evaporated TiAlN coatings and three different substrate materials, i.e. high PCBN content polycrystalline cubic boron nitride (PCBN),cemented carbide(CC) and high speed steel(HSS). all substrate resources can be view as hard, they outcome in completely diverse coating breakdown mechanisms at the common load consequential to substrate experience. moreover, coating failure resulting in substrate introduction does not necessarily keep in touch to interfacial cracking consequential in adhesive fracture along the outside layer substrate boundary. The results illuminate the importance of understanding the effect of different types of lapping/grinding processes in the pre-treatment of hard and super hard sub strate materials and the amount and type of damage that they can create.

A. Pilkington et al (2013)⁽³⁷⁾The normal number of 2. 5D blind outlets drilled by AlCrOxN 1-x covered M2 jobber make a hole sin D2 device steel was found

to be associated to the coating rigidity. The coatings put down onto M2 HSS drills by way of a N₂/O₂ relation of 0.9/0.1 achieve better than covering completed with the 0.75/0.25N₂/O₂ percentage. The greater covering thickness of the AlCrON covered drills is the most important cause for the advanced number of puncture drilled in association to the AlCrN covered drills. Pulse bias covering had a longer living point in time than DC partiality coatings for like reactive gas declaration ratios. The lowest devotion of Fe-Cr-Ni was establishing on the DC 0.75 N₂ 0.25O₂ covering which explain the lowest turn wear.

Dirk Biermanna et al (2013)⁽³⁸⁾Diverse hard coatings for the micro grinding of the austenitic stainless steel X5CrNi18- 10 were examined by revenue of the process services, the device wear in addition to the available surface quality. linking to the device wear, the AlCrN with TiAlN covering produced the most excellent outcomes. Due to their inadequate hardness TiN with CrN coated apparatus could not be capable for this machining work. The CrN coatings show signs of severe spalling of the covering since of the chemical reactivity of the coating of outer layer and the work piece substance.

Halil C- ahs-kan et al (2013)⁽³⁹⁾The nc-TiAlSiN/TiSiN/TiAlN has 1.7 times higher ratio than the nano layered coating and it is the most resistant coating to plastic deformation among the used coatings due to its high hardness and low Young's modulus. The single layer TiN coating exhibited superior performance than all the other coatings and gave the lowest wear rate. The nc TiAlSiN/TiSiN/TiAlN coating, which has the highest hardness among the coatings, had the highest specific wear rate.

W. Henderer et al (2013)⁽⁴⁰⁾TiSiN+CrCx/C coated taps have better wear resistance than TiN+CrC/C and DLC coatings. Higher hardness levels can be achieved with Ti targets containing 15 at.% Si, the optimum cutting tool wear resistance was achieved with 5 at.% Si targets. Further work is required to improve the surface finish from cathodic arc deposition processes for Ti-Si-N coatings.

G.K. Dosbaeva et al (2014)⁽⁴¹⁾ The cutting temperature measured by the tool work piece thermocouple on the wear characteristics of carbide device with the CVD multilayer TiCN with Al₂O₃ coating, along with low element Polycrystalline Cubic Boron Nitride utensils in turning toughened D2 instrument steel. When growing the cutting speed to 175 m/min, and consequently the cutting heat to over

1100 OC, these tribo-films develop into unsuccessful, and PCBN has the extended instrument living due to its higher hot rigidity. Adhesive as well as chemical wear can be measured the most important wear mechanisms in the used PCBN cutting device.

Yin-Yu Chang et al (2014)⁽⁴²⁾The Si containing TiAlSiN coatings have better oxidation resistance compared to the TiAlN. All the deposited coatings exhibited good adhesion strength (HF1– HF2 ranking according to VDI 3198 standard) on the tungsten carbide tools. It showed that the $\text{Cr}_{0.47}\text{Al}_{10.46}\text{Si}_{0.07}\text{N}$ and $\text{Ti}_{0.55}\text{Al}_{0.40}\text{Si}_{0.05}\text{N}$ possessed higher thermal stability than $\text{Ti}_{0.52}\text{Al}_{0.48}\text{N}$. It is confirmed in the dry cutting tests that the multi component coatings are useful at high speed machining of the Ti–6Al–4V alloys.

Youqiang Xing et al (2014)⁽⁴³⁾The cutting performance of the WS₂/Zr coated tools and WS₂/Zr coated nano-textured tools is significantly improved compared with the conventional Al₂O₃/TiC ceramic cutting tools. The nano-textured Al₂O₃/TiC ceramic cutting tools deposited with WS₂/Zr composite soft coatings are more effective in reducing the cutting force, cutting temperature, friction coefficient and tool wear compared with the WS₂/Zr coated tool without nano-textures on its rake face.

A.Thakur et al (2014)⁽⁴⁴⁾Coated tool on the other hand helps to prevent severe escalation of temperature, but at the same time results in a thermally dominated layer (due to lower thermal conductivity of Al₂O₃ coating as explained before) possessing less hardness. Therefore, it may be concluded that CVD multilayer coating has synergistic influence on the improvement of the machined surface integrity-based super alloy (Inconel 825).

CONCLUSION

Nitride based ternary thin films like TiAlN and CrN has great demand in industrial applications, as it gives better film properties like high hardness, low coefficient of friction, good wear resistance and excellent corrosion protection, high melting point etc. as compared to binary nitride compounds (e.g. TiN, MoN, VN). In the present work the performance of coated tools in machining hardening steel under dry conditions is studied. The results shows that the TiAlN and CrN coated tool perform better as compared to uncoated cutting tool. The effect of cutting is to reduce wear and tear of tool tip point hence the increase in tool life. After the Experimental Coated tools performance best to uncoated tools.

REFERENCES

- (1) K.S. Rajam, B. Deepthi ,H.C. Barshilia, Vacuum 81 (2006) 479–488.
- (2) M. Andritschky, F. Vaz, L. Rebouta, J.C Soares, M.F da Silva, J. Mater. Process. Technol. 92–93 (1999) 169.
- (3) J. Vac., W.D. Munz, Sci. Technol. A 4 (1986) 2717.
- (4) K. Yamamoto, G.S. Fox-Rabinovich, S.C. Veldhuis, G.K. Dosbaeva, A.I. Kovalev, Surf. Coat. Technol. 200 (2005) 1804.
- (5) D. Rafaja, et al., Surf. Coat. Technol. 201 (2007) 9476–9484.
- (6) A.K. Hashimoto, T. Suzuki, M. Kawate, Surf. Coat. Technol. 165 (2003) 163.
- (7) C.H. Mitterer, B. Sartory, A.E. Reiter, J. Vac. Sci. Technol. A: Vac. Surf. Films 25(2007) 711.
- (8) A.S. Argon, R.F. Zhang, S. Veprek, Phil. Mag. Lett. 87 (2007) 955.
- (9) J.G. Maritza, S. Veprek, Veprek-Heijman, Surf. Coat. Technol. 202 (2008) 5063–5073.
- (10) M.G. Faga, L. Settineri, G. Gautier, M. Perucca, CIRP Ann. Manuf. Technol. 57 (2008) 575–578.
- (11) S. Imamura, et al., Surf. Coat. Technol. 202 (2007) 820–825.
- (12) M. Hagarova, O. Blahova, J. Savkova, Acta Metall. Slovaca 15 (4) (2009) 221–227, ISSN1338-1156.
- (13) M. Hagarova, J. Met. Mater. Miner. 17 (2) (2007) 29–35, ISSN 0857-6149.
- (14) Yang Leng, Hong Kong University of Science and Technology, "Materials Characterization Introduction to Microscopic and Spectroscopic Methods", ISBN 978-0-470-82298-2
- (15) J. Nickel ,A.N. Shuaib, B.S. Yilbas ,S.M. Nizam, "Evaluation of the wear of plasma-nitrided and TiN-coated HSS drills using conventional and Micro-PIXE techniques", Wear, 2000, 239, 155–167
- (16) J. Wang, "The effect of the multi-layer surface coating of carbide inserts on the cutting forces in turning operations", Materials Processing Technology, 2000, 97, 114-119
- (17) V. Fox, A. Jones, N.M. Renevier , D.G. Teer, "Hard lubricating coatings for cutting and forming tools and mechanical components", Surface and Coatings Technology, 2000, 125, 347–353

- (18) G.S. Fox-Rabinovich, N.A. Bushe, A.I. Kovalev, S.N. Korshunov, L.Sh. Shuster, G.K. Dosbaeva, "Impact of ion modification of HSS surfaces on the wear resistance of cutting tools with surface engineered coatings" *Wear*, 2001, 249, 1051–1058.
- (19) J. Richter, J. Cwajna, J. Szala, "Quantitative assessment of new high speed steel substrate and PVD wear resistant coatings", *Materials Characterization*, 2001, 46, 137–142.
- (20) L.A. Dobrzańska, K. Gołombka, J. Kopańc, M. Soković, "Effect of depositing the hard surface coatings on properties of the selected cemented carbides and tool cermets", *Materials Processing Technology*, 2004, 157–158, 304–311.
- (21) G.S. Fox-Rabinovich, S.C. Veldhuis, G.C. Weatherly, A.I. Kovalev, S.N. Korshunov, V.N. cvortsov, G.K. Dosbaeva, L.Sh. Shustere, D.L. Wainstein, "Improvement of duplex PVD coatings for HSS cutting tools by ion mixing", *Surface & Coatings Technology*, 2004, 187, 230–237.
- (22) A.E. Reiter, B. Brunner, M. Ante, J. Rechberger, "Investigation of several PVD coatings for blind hole tapping in austenitic stainless steel", *Surface & Coatings Technology*, 2006, 200, 5532–5541.
- (23) Fehim Findik, Erdal Celik, Recep Yigit, Sakip Koksak, "Tool life performance of multilayer hard coatings produced by HTCVD for machining of nodular cast iron", *Refractory Metals & Hard Materials*, 2008, 26, 514–524.
- (24) J. Gertha, M. Larsson, U. Wiklund, F. Riddara, S. Hogmark, "On the wear of PVD-coated HSS hobs in dry gear cutting", *Wear*, 2009, 266, 444–452.
- (25) M. Soković, B. Barišić, S. Sladić, "Model of quality management of hard coatings on ceramic cutting tools", *Materials Processing Technology*, (2009), 209, 4207–4216.
- (26) F. Qina, Y.K. Chou, D. Nolen, R.G. Thompson, "Coating thickness effects on diamond coated cutting tools", *Surface & Coatings Technology*, 2009, 204, 1056–1060.
- (27) M.A. ElHakim, M.D. Abad, M.M. Abdelhameed, M.A. Shalaby, S.C. Veldhuis, "Wear behavior of some cutting tool materials in hard turning of HSS", *Tribology International*, 2011, 44, 1174–1181.
- (28) A.S.H. Basari, A.S.M. Jaya, M.R. Muhamad, M.N.A. Rahman, S.Z.M. Hashim, H. Haron, "Application of ANFIS in predicting TiAlN coatings flank wear", *International Conference on Computational Intelligence, Modeling & Simulation*, 2011.
- (29) D. Jakubčzyová, P. Hvizdoš, M. Selecká, "Investigation of thin layers deposited by two PVD techniques on high speed steel produced by powder metallurgy", *Applied Surface Science*, 2012, 258, 5105–5110.
- (30) Turgay Kivak, Gürcan Samtas, Adem Çiçek, "Taguchi method based optimisation of drilling parameters in drilling of AISI 316 steel with PVD monolayer and multilayer coated HSS drills", 2012, *Measurement*, 45, 1547–1557.
- (31) J. Heinrichs, J. Gerth, U. Bexell, M. Larsson, U. Wiklund, "Influence from surface roughness on steel transfer to PVD tool coatings in continuous and intermittent sliding contacts", *Tribology International*, 2012, 56, 9–18.
- (32) Serge N. Grigorieva, A.A. Vereschaka, A.S. Vereschaka, A.A. Kiting, "Cutting tools made of layered composite cermet, mica with nano-scale multilayered coatings", *Proscenia CIRP*, 2012, 1, 301–306.
- (33) Ping Chuan Siowa, Jaharah A. Ghanian, Mariyam Jameelah Ghazalia, Talib Ria-Jaafar, Mohamad Asri Selamat, Che Hassan Che Harona, "Characterization of TiCN and TiCN/ZrN coatings for cutting tool application", *Ceramics International*, 2013, 39, 1293–1298.
- (34) J. Heinrichs, J. Gerth, T. Thersleff, U. Bexell, M. Larsson, U. Wiklund, "Influence of sliding speed on modes of material transfer of steel slides against PVD tool coatings", *Tribology International*, 2013, 58, 55–64.
- (35) D. Kottfer, M. Ferdinandy, L. Kaczmarek, I. Maňková, J. Beňová, "Investigation of Ti and Cr based PVD coatings deposited onto HSS Co5 twist drills", *Applied Surface Science*, 2013, 282, 770–776.
- (36) S. Sveen, J.M. Andersson, R.M. Saoubi, M. Olsson, "Scratch adhesion characteristics of PVD TiAlN deposited on high speed steel, cemented carbide and PCBN substrates", *Wear*, 2013, 308, 133–141.

- (37) A.Pilkington , S.J.Dowey ,J.T.Toton ,E.D.Doyle, " Machining with AlCr oxinitride PVD coated cutting tools", Tribology International, 2013, 65, 303–313
- (38) Dirk Biermanna, Markus Steiner, Eugen Krebs, "Investigation of Different Hard Coatings for Micromilling of Austenitic Stainless Steel", ProsceniaCIRP , 2013 ,7, 246 – 251
- (39) HalilC-als-kan,CahitKurbanoğlu, PeterPanjan,MihaČekada,DavorinKramar "Wear behavior and cutting performance of nanostructured hard coatings on cemented carbide cutting tools in hard milling", Tribology International, 2013,62, 215–222
- (40) W. Henderer , F. Xu, "Hybrid TiSiN, CrC/C PVD coatings applied to cutting tools", Surface & Coatings Technology, 2013,215, 381–385
- (41) G.K. Dosbaeva, M.A. El Hakim, M.A. Shalaby, J.E. Krzanowski, S.C.Veldhuis, "Cutting temperature effect on PCBN and CVD coated carbide tools in hard turning of D2 tool steel", Refractory Metals and Hard Materials ,2014
- (42) Yin-Yu Chang , Hsing-Ming Lai, "Wear behavior and cutting performance of Carlson and TiAlSiN hard coatings on cemented carbide cutting tools for Ti alloys", Surface & Coatings Technology, 2014
- (43) YouqiangXing, JianxinDeng n, ShipengLi, HongzhiYue, RongMeng, PengGao, "Cutting performance and wear characteristics of Al₂O₃/TiC ceramic cutting tools with WS₂/Zr soft-coatings and nano-textures in dry cutting", wear, 2014, 318,12–26
- (44) A.Thakur, S.Gangopadhyay*, K.P.Maity, "Effect of cutting speed and tool coating on machined surface integrity of Ni-based super alloy", ProsceniaCIRP, 2014, 14, 541 – 545