

## CARBON FIBER FABRIC GG240T

Setting (Thr/cm): 6,0/6,0  
 Weave: Twill 2/2  
 Finish: loomstate

<u>Construction:</u>	Warp	Weft
Yarn material <sup>1)</sup> :	Carbon 3K	Carbon 3K
Yarn number <sup>1)</sup> :	200 tex	200 tex

<u>Technical Data:</u>		Unit	Target	+/-	Tolerance
Fibre density <sup>1) 3)</sup>	Warp	g/cm <sup>3</sup>	n.G.	+/-	n.G.
	Weft	g/cm <sup>3</sup>	n.G.	+/-	n.G.
Linear density <sup>1)</sup>	Warp	tex	200	+/-	10
	Weft	tex	200	+/-	10
Twist <sup>1)</sup>	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	Thr./cm	6,0	+/-	0,3
	Weft	Thr./cm	6,0	+/-	0,3
Weave			Twill 2/2		
Weight		g/m <sup>2</sup>	245	+/-	10
Dry weight		g/m <sup>2</sup>	245	+/-	10
Moisture content		%	0,5	+/-	max.
Thickness <sup>2)</sup>		mm	0,35	+/-	
Width		cm	as ordered	+/-	1

<sup>1)</sup> = n.G. = depending on order and yarn specification

<sup>3)</sup> = no measure, certified by supplier

<sup>2)</sup> = approximate value, not for release